

Double layer high-temperature resistant red silicone hose

Product images	Application	Characteristic	Structure
	▶ Cold and hot air suction	▶ Soft and gentle texture	▶ Color: Red/Black
	▶ Smoke suction and exhaust	▶ High temperature resistance	▶ Temperature: -70 ℃/+270 ℃
		▶ Smooth inner wall with low wind resistance	Short term temperature resistance+300 ℃
		▶ Strong elasticity and flexibility	▶ Installation requirements:
▶ Hose wall: double-layer silicone coated fiberglass cloth		▶ Environmentally friendly and non-toxic	Avoid surface friction and stay away from strong chemical corrosiveness
▶ Reinforcement: Spiral steel wire+high temperature resistant fiberglass wire			

Part Number	Internal Diameter mm	Outside diameter mm	Weight kg/4m	Working Pressure bar	Vacuum bar	Bending Radius mm	Coil Length m
502-013-4	13	16	0.35	3.00	0.74	10	4
502-016-4	16	19	0.44	3.00	0.74	12	4
502-019-4	19	22	0.50	3.00	0.73	13	4
502-022-4	22	25	0.53	3.00	0.72	14	4
502-025-4	25	28	0.60	2.80	0.71	18	4
502-032-4	32	35	0.65	2.70	0.65	20	4
502-038-4	38	41	0.76	2.60	0.60	24	4
502-040-4	40	43	0.80	2.60	0.60	26	4
502-042-4	42	45	0.85	2.60	0.59	26	4
502-044-4	44	48	0.95	2.60	0.58	27	4
502-045-4	45	49	1.00	2.60	0.58	27	4
502-050-4	50	54	1.05	2.60	0.52	31	4
502-051-4	51	55	1.10	2.60	0.52	31	4
502-057-4	57	61	1.26	2.50	0.48	34	4
502-060-4	60	64	1.32	2.50	0.48	34	4
502-063-4	63	67	1.40	2.40	0.46	37	4
502-070-4	70	75	1.50	2.10	0.44	40	4
502-076-4	76	81	1.60	2.10	0.43	43	4
502-080-4	80	85	1.65	2.10	0.42	45	4
502-083-4	83	88	1.72	2.10	0.41	47	4
502-089-4	89	94	1.80	2.00	0.40	50	4
502-102-4	102	107	1.98	1.90	0.35	56	4
502-108-4	108	113	2.10	1.80	0.33	60	4
502-110-4	110	115	2.20	1.80	0.33	60	4
502-115-4	115	120	2.44	1.50	0.30	63	4
502-127-4	127	133	2.56	1.50	0.23	70	4
502-141-4	141	147	2.70	1.30	0.20	76	4
502-150-4	150	156	3.00	1.20	0.17	82	4
502-152-4	152	158	3.06	1.20	0.17	82	4
502-159-4	159	165	3.20	1.10	0.16	86	4
502-164-4	164	170	3.40	1.10	0.14	89	4
502-169-4	169	176	3.60	1.10	0.14	89	4
502-180-4	180	187	3.90	1.00	0.12	95	4
502-203-4	203	210	4.48	0.70	0.09	108	4
502-254-4	254	261	5.58	0.50	0.07	133	4
502-306-4	306	313	7.00	0.50	0.07	159	4

Note: * All technical parameters are approximate values and measured under conditions of 23 ℃ operating temperature and 50% ambient humidity. They may change accordingly based on actual operating conditions.

* We will periodically revise or adjust the relevant parameters. If we are unable to notify in a timely manner, please forgive us and refer to the data published on the website or company.